

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:


LISTING OF CLAIMS:

1. (original): A light emitting element comprising at least one organic layer which includes a light emitting layer, and which is disposed between a pair of electrodes, wherein at least one layer of the at least one organic layer contains at least one compound consisting essentially of carbon, fluorine and silicon.

2. (previously presented): The light emitting element of claim 1, wherein said at least one compound consisting essentially of carbon, fluorine and silicon contains hydrogen atoms in an amount of not greater than two hydrogen atoms per six carbon atoms.

3. (previously presented): The light emitting element of claim 1, wherein said at least one compound consisting essentially of carbon, fluorine and silicon is represented by the following general formula (I):

General formula (I)




wherein in general formula (I), each of Ar¹, Ar², Ar³ and Ar⁴ represents an aryl group consisting of carbon and fluorine.

4. (original): The light emitting element of claim 3, wherein each of Ar¹, Ar², Ar³ and Ar⁴ in general formula (I) is selected from the group consisting of a perfluorophenyl group, a perfluorobiphenyl group, a perfluoronaphthyl group, a perfluoroanthracenyl group, a perfluorophenanthryl group, a perfluoropyrenyl group, a perfluoronaphthacenyl group and a perfluoroperylenyl group.

5. (previously presented): The light emitting element of claim 1, wherein said at least one compound consisting essentially of carbon, fluorine and silicon is represented by the following general formula (II):

General formula (II)



wherein in general formula (II), Ar²¹, Ar²², Ar²³, Ar²⁴, Ar²⁵ and Ar²⁶ each independently represent an aryl group consisting of carbon and fluorine; and L represents a divalent arylene group consisting of carbon and fluorine.

6. (original): The light emitting element of claim 5, wherein each of Ar²¹, Ar²², Ar²³, Ar²⁴, Ar²⁵ and Ar²⁶ in the general formula (II) is selected from the group consisting of a perfluorophenyl group, a perfluorobiphenyl group, a perfluoronaphthyl group, a perfluoroanthracenyl group, a perfluorophenanthryl group, a perfluoropyrenyl group, a perfluoronaphthacenyl group and a perfluoroperylenyl group.

7. (previously presented): The light emitting element of claim 1, wherein said at least one compound consisting essentially of carbon, fluorine and silicon has a glass transition temperature in a range of 130°C to 400°C.

8. (original): The light emitting element of claim 1, wherein light emission from an excited triplet state is utilized.

9. (previously presented): The light emitting element of claim 8, wherein said at least one compound consisting of carbon, fluorine and silicon has a minimum excited triplet energy level of 65 kcal/mol (272.35 kJ/mol) to 95 kcal/mol (398.05 kJ/mol) when light emission from an excited triplet state is utilized.

10. (previously presented): The light emitting element of claim 1, wherein said at least one compound consisting essentially of carbon, fluorine and silicon is used as an electron transporting material.

11. (previously presented): The light emitting element of claim 10, wherein said at least one compound consisting essentially of carbon, fluorine and silicon, which is used as an electron transporting material, is contained in a amount of 60 to 100% by mass in an organic layer containing the electron transporting material.

12. (previously presented): The light emitting element of claim 1, wherein said at least one compound consisting essentially of carbon, fluorine and silicon is used as a host material in a layer containing a light emitting material.

13. (original): The light emitting element of claim 12, wherein the compound, which is used as a host material, is contained in an amount of 50 to 99.9% by mass in an organic layer containing the host material.

14. (original): The light emitting element of claim 1, wherein the at least one organic layer contains a phosphorescent material.

15. (original): The light emitting element of claim 14, wherein the phosphorescent material is a transition metal complex.

16. (original): The light emitting element of claim 15, wherein the transition metal complex is selected from the group consisting of an iridium complex, a platinum complex, a rhenium complex and a ruthenium complex.

17. (original): The light emitting element of claim 16, wherein the transition metal complex is an iridium complex.

18. (original): The light emitting element of claim 1, wherein the at least one organic layer is formed by a resistance heating vapor deposition method, a coating method or a transferring method.

19. (original): The light emitting element of claim 1, wherein the light emitting layer is formed by a coating method.

20. (canceled).

21. (canceled).

22. (canceled).

23. (canceled).

24. (canceled).

25. (canceled).

26. (canceled).

27. (previously presented): A light emitting element comprising a pair of electrodes and at least one organic layer which includes a light emitting layer, and which is disposed between said pair of electrodes, wherein at least one layer of the at least one organic layer contains at least one compound consisting of carbon, fluorine and silicon.

28. (previously presented): The light emitting element of claim 27, wherein the at least one compound consisting of carbon, fluorine and silicon has a glass transition temperature in a range of 130°C to 400°C.

29. (previously presented): The light emitting element of claim 27, wherein the at least one compound consisting of carbon, fluorine and silicon has a minimum excited triplet energy level of 65 kcal/mol (272.35 kJ/mol) to 95 kcal/mol (398.05 kJ/mol) when light emission from

an excited triplet state is utilized.

30. (previously presented): The light emitting element of claim 27, wherein the at least one compound consisting of carbon, fluorine and silicon is used as an electron transporting material.

31. (previously presented): The light emitting element of claim 27, wherein the at least one compound consisting of carbon, fluorine and silicon is used as a host material in a layer containing a light emitting material.

32. (previously presented): The light emitting element of claim 27, wherein the at least one organic layer further contains a phosphorescent material.

33. (previously presented): The light emitting element of claim 32, wherein the phosphorescent material is a transition metal complex.